

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
6 April 2006 (06.04.2006)

PCT

(10) International Publication Number
WO 2006/036251 A1

(51) International Patent Classification⁷: **H01L 33/00**

(21) International Application Number:
PCT/US2005/023874

(22) International Filing Date: 5 July 2005 (05.07.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/947,704 23 September 2004 (23.09.2004) US

(71) Applicant (for all designated States except US): **CREE, INC.** [US/US]; 4600 Silicon Drive, Durham, NC 27703 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **NEGLEY, Gerald, H.** [US/US]; 306 N. Estes Drive, Estes Park, Apt. I-14, Cariboro, NC 27510 (US).

(74) Agents: **BIGEL, Mitchell, S. et al.**; Myers Bigel Sibley & Sajovec, P.A., P.O. Box 37428, Raleigh, NC 27627 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: SEMICONDUCTOR LIGHT EMITTING DEVICES INCLUDING PATTERNABLE FILMS COMPRISING TRANSPARENT SILICONE AND PHOSPHOR, AND METHODS OF MANUFACTURING SAME



(57) Abstract: Semiconductor light emitting devices include a semiconductor light emitting element having a light emitting surface, and a patternable film including transparent silicone and phosphor on at least a portion of the light emitting surface. The patternable film may be a photopatternable film and/or a printable film including transparent silicone and phosphor. The patternable film includes an aperture therein that exposes a portion of a light emitting surface, and a bond pad is provided on the light emitting surface in the aperture. A wire bond may be provided on the bond pad. Related methods of fabricating semiconductor light emitting devices are also provided.

0 2006/036251 A1

**SEMICONDUCTOR LIGHT EMITTING DEVICES INCLUDING
PATTERNABLE FILMS COMPRISING TRANSPARENT SILICONE AND
PHOSPHOR, AND METHODS OF MANUFACTURING SAME**

Field of the Invention

This invention relates to microelectronic devices and fabrication methods therefor, and more particularly to semiconductor light emitting devices and fabrication methods therefor.

5

Background of the Invention

Semiconductor light emitting devices, such as Light Emitting Diodes (LEDs) or laser diodes, are widely used for many applications. As is well known to those having skill in the art, a semiconductor light emitting device includes a semiconductor light emitting element having one or more semiconductor layers that are configured to emit coherent and/or incoherent light upon energization thereof. It is also known that a semiconductor light emitting device generally is packaged to provide external electrical connections, heat sinking, lenses or waveguides, environmental protection and/or other functions.

Continued developments in LEDs have resulted in highly efficient and mechanically robust light sources that can cover the visible spectrum and beyond. These attributes, coupled with the potentially long service life of solid state devices, may enable a variety of new display applications, and may place LEDs in a position to compete with the well entrenched incandescent and fluorescent lamps.

It may be desirable to provide a phosphor for an LED, for example to provide solid-state lighting. In one example, LEDs that are used for solid-state white lighting may produce high radiant flux output at short wavelengths, for example in the range of about 380nm to about 480nm. One or more phosphors may be provided, wherein the short wavelength, high energy photon output of the LED is used to excite the phosphor, in part or entirely, to thereby down-convert in frequency some or all of the LED's output to create the appearance of white light.

As one specific example, ultraviolet output from an LED at about 390nm may be used in conjunction with red, green and blue phosphors, to create the appearance of white light. As another specific example, blue light output at about 470nm from an

LED may be used to excite a yellow phosphor, to create the appearance of white light by transmitting some of the 470nm blue output along with some secondary yellow emission occurring when part of the LEDs output is absorbed by the phosphor.

As is well known to those having skill in the art, at least two techniques may be used to incorporate phosphor material into a light emission path of an LED. In one technique, the phosphor may be suspended in the packaging and/or encapsulation that is provided with the LED, so that the phosphor is maintained in proximity to the LED. In an alternative approach, the phosphor material is coated on the LED itself. When coating a phosphor, a liquid binder, such as an epoxy, may be used, in which one or more phosphors is suspended. The phosphor-containing binder may be dispensed onto the LED prior to dispensing and curing a clear encapsulation epoxy. LEDs that employ phosphor coatings are described, for example, in U.S. Patents, 6,252,254; 6,069,440; 5,858,278; 5,813,753; and 5,277,840. Moreover, published United States Patent Application No. US 2004/0056260 A1, published on March 25, 2004, entitled *Phosphor-Coated Light Emitting Diodes Including Tapered Sidewalls, and Fabrication Methods Therefor*, the disclosure of which is hereby incorporated herein by reference in its entirety as if set forth fully herein, describes a light emitting diode that includes a substrate having first and second opposing faces and a sidewall between the first and second opposing faces that extends at an oblique angle from the second face towards the first face. A conformal phosphor layer is provided on the oblique sidewall. The oblique sidewall can allow more uniform phosphor coatings than conventional orthogonal sidewalls.

Summary of the Invention

Semiconductor light emitting devices according to embodiments of the present invention include a semiconductor light emitting element that includes a light emitting surface, and a patternable film comprising transparent silicone and phosphor on at least a portion of the light emitting surface. The patternable film comprising transparent silicone and phosphor may be a photopatternable film and/or a printable film comprising transparent silicone and phosphor. In some embodiments, the patternable film comprising transparent silicone and phosphor includes an aperture therein that exposes a light emitting surface, and a bond pad is provided on the light emitting surface in the aperture. In other embodiments, a wire bond is provided on the bond pad opposite the light emitting surface.

In still other embodiments, the light emitting surface includes a face and a sidewall that extends from the face, and the patternable film comprising transparent silicone and phosphor is on at least a portion of the face and on at least a portion of the sidewall. Moreover, in some embodiments, the patternable film comprising
5 transparent silicone and phosphor is thicker, and in some embodiments at least 10% thicker, on at least a portion of the sidewall than on at least a portion of the face.

In yet other embodiments, the phosphor is configured to convert at least some light that is emitted from the light emitting surface, such that light that emerges from the semiconductor light emitting device appears as white light. In other embodiments,
10 a patternable film comprising transparent silicone and free of phosphor is provided between the light emitting surface and the transparent patternable film comprising silicone and phosphor.

In yet other embodiments of the present invention, a second semiconductor light emitting element is monolithically integrated with a first semiconductor light
15 emitting element, and the patternable film comprising transparent silicone and phosphor is provided on at least a portion of the light emitting surfaces of both the first and second monolithically integrated semiconductor light emitting elements. In still other embodiments, first and second semiconductor light emitting elements are provided on a mounting tape and spaced apart from one another, and the patternable
20 film comprising transparent silicone and phosphor is provided on at least a portion of the light emitting surfaces of both the first and second semiconductor light emitting elements. In other embodiments, the patternable film comprising transparent silicone and phosphor also extends onto the mounting tape between the spaced apart first and second light emitting devices. In still other embodiments, the light emitting surfaces
25 include sidewalls facing one another, and the patternable film comprising transparent silicone and phosphor extends onto at least a portion of the face and sidewalls.

In still other embodiments of the present invention, multiple layers of patternable films comprising transparent silicone and phosphor may be provided on at least a portion of the light emitting surface. In some embodiments, the phosphors in
30 the various layers may be the same. However, in other embodiments, a first phosphor may be provided in a first film and a second phosphor may be provided in a second film. For example, the first phosphor may be a green phosphor, and the second phosphor may be a red phosphor. Yet other combinations of two or more patternable films also may be provided.

Semiconductor light emitting devices may be fabricated, according to various embodiments of the present invention, by coating a patternable film comprising transparent silicone and phosphor on at least a portion of a light emitting surface of a semiconductor light emitting element. In some embodiments, a photopatternable film
5 comprising transparent silicone and phosphor is coated on at least a portion of the light emitting surface of a semiconductor light emitting diode. In other embodiments, a printable film comprising transparent silicone and phosphor is printed on at least a portion of a light emitting surface of a semiconductor light emitting element. In some embodiments, the photopatternable film comprising transparent silicone and phosphor
10 is photopatterned to form an aperture therein that exposes a light emitting surface. In other embodiments, the printable film comprising transparent silicone and phosphor is printed on at least a portion of the light emitting surface of the semiconductor light emitting element, to define an aperture therein that exposes the light emitting surface. In yet other embodiments, a bond pad is formed on the light emitting surface of the
15 aperture, and, in still other embodiments, a wire is bonded to the bond pad opposite the light emitting surface.

In some embodiments, coating is performed such that the patternable film comprising transparent silicone and phosphor is coated on at least a portion of the face of the light emitting surface and on at least a portion of a sidewall thereof. In some
20 embodiments the coating is thicker, and, in some embodiments, at least 10% thicker, on at least a portion of the sidewall than on at least a portion of the face.

In some embodiments of the invention, photopatterning is performed by selectively exposing the photopatternable film comprising transparent silicone and phosphor to define the aperture, and then developing the photopatternable film
25 comprising transparent silicone and phosphor that has been exposed, to form the aperture. In still other embodiments, the photopatternable film comprising transparent silicone and phosphor is again developed to enlarge the aperture. In yet other embodiments, light emission of a light emitting device is measured after developing the photopatternable film comprising transparent silicone, and phosphor and a second
30 development is performed if the light emission of the light emitting device that is measured does not conform to at least one predefined parameter, such as an emission frequency spectrum. In still other embodiments, a photopatternable film comprising transparent silicone and free of phosphor may be coated on at least a portion of the

light emitting surface prior to coating the photopatternable film comprising transparent silicone and phosphor.

Method embodiments of the present invention also may be used to coat multiple semiconductor light emitting elements. In some embodiments, the patternable film comprising transparent silicone and phosphor is coated on at least a portion of multiple semiconductor light emitting elements that are monolithically integrated. In other embodiments a plurality of semiconductor light emitting devices are mounted on a mounting tape, and the multiple semiconductor light emitting devices on a mounting tape are then coated. In still other embodiments, the mounting tape is stretched prior to coating to define spaces between adjacent devices, and then coating is performed on the devices and on the spaces therebetween. In yet other embodiments, sidewalls of the devices also are coated.

Yet other method embodiments of the present invention may coat more than one patternable film comprising transparent silicon and phosphor on at least a portion of the light emitting surface. In particular, in some embodiments, a patternable film comprising transparent silicone and a first phosphor is first coated on the light emitting surface. Then, a second patternable film comprising transparent silicone and a second phosphor is coated on the first patternable film comprising transparent silicone and a first phosphor. In some embodiments, the first phosphor is a green phosphor and the second phosphor is a red phosphor. Yet other combinations of two or more patternable films also may be provided.

Brief Description of the Drawings

Figures 1-6 are cross-sectional views of semiconductor light emitting devices according to various embodiments of the present invention.

Figures 7-9 are flowcharts illustrating manufacturing methods for semiconductor light emitting devices according to various embodiments of the present invention.

Detailed Description

The present invention now will be described more fully hereinafter with reference to the accompanying drawings, in which embodiments of the invention are shown. However, this invention should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this

disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art. In the drawings, the thickness of layers and regions are exaggerated for clarity. Like numbers refer to like elements throughout. As used herein the term "and/or" includes any and all combinations of one or more of
5 the associated listed items.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the invention. As used herein, the singular forms "a", "an" and "the" are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the
10 terms "comprises" and/or "comprising," when used in this specification, specify the presence of stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

It will be understood that when an element such as a layer or region is referred
15 to as being "on" or extending "onto" another element, it can be directly on or extend directly onto the other element or intervening elements may also be present. In contrast, when an element is referred to as being "directly on" or extending "directly onto" another element, there are no intervening elements present. It will also be understood that when an element is referred to as being "connected" or "coupled" to
20 another element, it can be directly connected or coupled to the other element or intervening elements may be present. In contrast, when an element is referred to as being "directly connected" or "directly coupled" to another element, there are no intervening elements present.

It will be understood that, although the terms first, second, etc. may be used
25 herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer or section from another region, layer or section. Thus, a first element, component, region, layer or section discussed below could be termed a second
30 element, component, region, layer or section without departing from the teachings of the present invention.

Furthermore, relative terms, such as "lower", "base", or "horizontal", and "upper", "top", or "vertical" may be used herein to describe one element's relationship to another element as illustrated in the Figures. It will be understood that relative

terms are intended to encompass different orientations of the device in addition to the orientation depicted in the Figures. For example, if the device in the Figures is turned over, elements described as being on the "lower" side of other elements would then be oriented on "upper" sides of the other elements. The exemplary term "lower", can
5 therefore, encompasses both an orientation of "lower" and "upper," depending of the particular orientation of the figure. Similarly, if the device in one of the figures is turned over, elements described as "below" or "beneath" other elements would then be oriented "above" the other elements. The exemplary terms "below" or "beneath" can, therefore, encompass both an orientation of above and below.

10 Embodiments of the present invention are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments of the present invention. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments of the present invention should not be construed as limited to the
15 particular shapes of regions illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated, typically, may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to
20 illustrate the precise shape of a region and are not intended to limit the scope of the present invention. Moreover, terms such as "horizontal", "vertical" and "perpendicular" indicate general directions or relationships rather than precise 0° or 90° orientations.

Unless otherwise defined, all terms (including technical and scientific terms)
25 used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense unless expressly so
30 defined herein.

Figure 1 is a cross-sectional view of a semiconductor light emitting device according to various embodiments of the present invention. Referring now to Figure 1, a semiconductor light emitting device 100 according to various embodiments of the present invention includes a semiconductor light emitting element 110 that includes a

light emitting surface 110a. A patternable film comprising transparent silicone and phosphor 120 is provided on at least a portion of the light emitting surface 110a. As used herein, "light" refers to any radiation, visible and/or invisible (such as ultraviolet) that is emitted by a semiconductor light emitting element 110. Moreover, as used herein, the term "transparent" means that at least some optical radiation that enters the patternable film comprising transparent silicone and phosphor 120 is emitted from the film 120.

Patternable films comprising transparent silicone are well known to those having skill in the art. For example, Dow Corning® markets a series of low stress patternable silicone materials, designated as Dow Corning WL-3010 Printable Silicone and Dow Corning WL-5000 series Photopatternable Spin-On Silicones. Dow Corning WL-3010 Printable Silicone is a stencil-printable paste material designed to provide a low stress, low-temperature-curable patterned silicone for a variety of microelectronics applications. Although Dow Corning WL-3010 paste material is black, transparent paste also may be provided and/or the paste may become transparent after curing. Dow Corning WL-5000 series Photopatternable Spin-On Silicones include WL-5150, WL-5350 and WL-5351 Photopatternable Spin-On Silicones, that are designed to provide low stress, low temperature-curable transparent patterned films for a variety of micro- and optoelectronics applications. As noted in a product information brochure entitled "*Information About Dow Corning® Brand Low-Stress Patternable Silicone Materials*", form no. 11-1108-01, copyright Dow Corning Corporation, 2003, these materials may have potential uses such as high-volume wafer level or other integrated circuit packaging applications; wafers, films, ceramics and laminates; stress-buffer layer applications; emerging applications using lead-free solder; front and backside wafer protective layers; redistribution layers; solder masks; negative photoresists; adhesive layers and sacrificial layers.

Phosphors also are well known to those having skill in the art. As used herein, the phosphor may be Cerium-doped Yttrium Aluminum Garnet (YAG:Ce) and/or other conventional phosphors and may be mixed into a paste or solution of transparent patternable film comprising silicone using conventional mixing techniques, to thereby provide the transparent patternable film comprising silicone and phosphor 120. In some embodiments, the phosphor is configured to convert at least some light that is emitted from the light emitting surface 110a such that light that emerges from the semiconductor light emitting device 100 appears as white light.

The semiconductor light emitting element 110 may include a light emitting diode, a laser diode and/or other semiconductor device that includes one or more semiconductor layers, which may include silicon, silicon carbide, gallium nitride and/or other semiconductor materials, a substrate which may include sapphire, silicon,
5 silicon carbide and/or other microelectronic substrates, and one or more contact layers, which may include metal and/or other conductive layers. In some embodiments, ultraviolet, blue and/or green LEDs may be provided. The design and fabrication of semiconductor light emitting devices are well known to those having skill in the art and need not be described in detail herein.

10 For example, light emitting devices according to some embodiments of the present invention may include structures such as the gallium nitride-based LED and/or laser structures fabricated on a silicon carbide substrate, such as those devices manufactured and sold by Cree, Inc. of Durham, North Carolina. The present invention may be suitable for use with LED and/or laser structures that provide active
15 regions such as described in United States Patent Nos. 6,201,262; 6,187,606; 6,120,600; 5,912,477; 5,739,554; 5,631,190; 5,604,135; 5,523,589; 5,416,342; 5,393,993; 5,338,944; 5,210,051; 5,027,168; 5,027,168; 4,966,862 and/or 4,918,497, the disclosures of which are incorporated herein by reference in their entirety as if set forth fully herein. Other suitable LED and/or laser structures are described in
20 published U.S. Patent Application Publication No. US 2003/0006418 A1 entitled *Group III Nitride Based Light Emitting Diode Structures With a Quantum Well and Superlattice, Group III Nitride Based Quantum Well Structures and Group III Nitride Based Superlattice Structures*, published January 9, 2003, as well as published U.S. Patent Application Publication No. US 2002/0123164 A1 entitled *Light Emitting*
25 *Diodes Including Modifications for Light Extraction and Manufacturing Methods Therefor*, the disclosures of which are hereby incorporated herein by reference in their entirety as if set forth fully herein. Furthermore, phosphor coated LEDs, such as those described in U.S. Application Serial No. 10/659,241, entitled *Phosphor-Coated Light Emitting Diodes Including Tapered Sidewalls and Fabrication Methods*
30 *Therefor*, filed September 9, 2003, the disclosure of which is incorporated by reference herein as if set forth fully, may also be suitable for use in some embodiments of the present invention. The LEDs and/or lasers may be configured to operate such that light emission occurs through the substrate. In such embodiments, the substrate may be patterned so as to enhance light output of the devices as is

described, for example, in the above-cited U.S. Patent Application Publication No. US 2002/0123164 A1.

Figure 2 is a cross-sectional view of semiconductor light emitting devices according to other embodiments of the present invention. As shown in Figure 2, the patternable film comprising transparent silicone and phosphor 120 includes an aperture 122 therein that exposes a portion of the light emitting surface 110a. When a photopatternable film is used, photolithography including exposure and development may be used to define the aperture, as will be described in detail below. In contrast, when a printable film is used, screen or stencil printing may be used to define the aperture while coating the printable film.

Still referring to Figure 2, a bond pad 130 is provided on the light emitting surface 110a in the aperture 122. As also shown, in some embodiments of the present invention, a wire bond 140 is provided on the bond pad 130 opposite the light emitting surface 110a. Bond pads and wire bonds are well known to those having skill in the art and need not be described further herein. One example of bond pads and wire bonds is described in Application Serial No. 10/899,793, filed July 27, 2004, entitled *Light Emitting Devices Having A Reflective Bond Pad And Methods Of Fabricating Light Emitting Devices Having Reflective Bond Pads*, assigned to the assignee of the present application, the disclosure of which is hereby incorporated herein by reference in its entirety as if set forth fully herein.

Accordingly, embodiments of the present invention can allow a phosphor to be coated on a semiconductor light emitting element prior to fabricating a bond pad and performing wire bonding. The patternable film comprising transparent silicone can be patterned using conventional printing or photolithographic techniques and can remain transparent even when exposed to the relatively high temperatures, such as temperatures of about 280°C or more that are used to fabricate a bond pad and perform a wire bond. Thus, by coating a semiconductor light emitting element with a patternable film comprising transparent silicone and phosphor according to some embodiments of the present invention, a layer of phosphor with a desired thickness and desired characteristics may be provided on a semiconductor light emitting element prior to fabricating a bond pad. This may allow the bond pad and wire bonding to take place without significantly degrading the operational characteristics of the semiconductor light emitting device.

Figure 3 is a cross-sectional view of semiconductor light emitting devices according to other embodiments of the present invention. As shown in Figure 3, the light emitting surface includes a face **110b** and at least one sidewall **110c** that extends from the face **110b**. The patternable film comprising transparent silicone and phosphor **120** is on at least a portion of the face **110b** and on at least a portion of the sidewall **110c**. Moreover, as also shown in Figure 3, in some embodiments of the present invention, the patternable film comprising transparent silicone and phosphor **120** is thicker on at least a portion of the sidewall **110c** than on at least a portion of the face **110b**. Thicker sidewall coatings thereby may be provided.

In fact, in some embodiments, the patternable film comprising silicone and phosphor is at least 10% thicker on at least a portion of the sidewall **110c** than on at least a portion of the face **110b**. Accordingly, some embodiments of the present invention can provide phosphor-coated light emitting devices including tapered sidewalls, wherein the coating can be thicker on the sidewalls **110c** compared to the face **110b** of the light emitting element. This may contrast sharply with conventional light emitting devices, such as described in U.S. Patent No. 6,642,652 to Collins III et al., in which variations in thickness of a phosphor coating are less than or equal to 10% of the average thickness. Heavily coated sidewall coatings thereby may be provided according to these embodiments of the present invention.

Figure 4 is a cross-sectional view of semiconductor light emitting devices according to yet other embodiments of the present invention. As shown in Figure 4, a patternable film comprising transparent silicone and free of phosphor **420** is provided between the light emitting surface **110a** and the patternable film comprising transparent silicone and phosphor **120**. In some embodiments, the film **420** may be provided by using any of the above-described Dow Corning brand low stress patternable silicone materials, without mixing phosphor therein. It will be understood, however, that other transparent patternable materials may be used and that other materials may be mixed in film **420** to provide light-scattering and/or other properties. Moreover, the same transparent patternable silicon material need not be used for films **120** and **420**.

Figure 5 is a cross-sectional view of semiconductor light emitting devices according to other embodiments of the present invention. As shown in Figure 5, a first semiconductor light emitting element **110** and a second semiconductor light emitting element **110'** are monolithically integrated, for example, by forming multiple

semiconductor light emitting elements in a wafer in a conventional manner. The first semiconductor light emitting element 110 includes a first light emitting surface 110a and the second semiconductor light emitting element 110' includes a second light emitting surface 110a'. As shown in Figure 5, the patternable film comprising transparent silicone and phosphor 120 is provided on at least a portion of both the first and second light emitting surfaces 110a, 110a'.

Figure 6 is a cross-sectional view of semiconductor light emitting devices according to yet other embodiments of the present invention. In Figure 6, first and second semiconductor light emitting elements 110 and 110' are mounted on a mounting tape 610. The mounting tape 610 may be a conventional "blue tape" that is conventionally used to hold diced semiconductor light emitting elements. As shown in Figure 6, the patternable film comprising transparent silicone and phosphor 120 is on at least a portion of the first and second light emitting surfaces 110a and 110a', respectively. Moreover, as shown in Figure 6, in some embodiments of the present invention, the first and second light emitting elements 110 and 110' are spaced apart from one another on the mounting tape 610, for example, by stretching the mounting tape 610 after the semiconductor light emitting elements 110, 110' are mounted thereon, to define a space 620 therebetween. The photopatternable film comprising transparent silicone and phosphor 120 extends onto the mounting tape 610 on the space 620 between the spaced apart first and second light emitting elements 110, 110'.

Moreover, as also shown in Figure 6, in yet other embodiments, the first light emitting surface 110a includes a first sidewall 110c facing the second semiconductor light emitting element 110', and the second light emitting surface 110a' includes a second sidewall 110c' facing the first semiconductor light emitting element 110. The patternable film comprising transparent silicone and phosphor 120 extends onto at least a portion of the first and second sidewalls 110c and 110c'. Thus, after dicing the individual light emitting devices 110, 110' and stretching the mounting tape 610, some embodiments of Figure 6 can produce embodiments of Figure 3, where the coating 120 is thicker on the sidewalls 110c than on the face 110b.

It will be understood by those having skill in the art that embodiments of Figures 1-6 may be provided in various combinations and subcombinations according to various other embodiments of the present invention.

Methods of fabricating semiconductor light emitting devices according to various embodiments of the present invention now will be described. For example,

referring to Figures 1 and 7, a semiconductor light emitting device 100 may be fabricated by coating a patternable film comprising transparent silicone and phosphor 120 on at least a portion of a light emitting surface 110a of a semiconductor light emitting element 110, as shown at Block 710 of Figure 7. In some embodiments of the invention, where the patternable film comprising transparent silicone and phosphor 120 is a printable film comprising silicone and phosphor, coating at Block 710 may be performed by stencil printing or screen printing equipment. Moreover, in embodiments of the invention where the patternable film comprising transparent silicone and phosphor 120 is a photopatternable film comprising silicone and phosphor, coating at Block 710 may be performed by, for example, spin-coating the photopatternable film comprising transparent silicone and phosphor.

Referring again to Block 710, according to other embodiments of the present invention, prior to coating the patternable film comprising transparent silicone and phosphor 120 on at least a portion of the light emitting surface of the semiconductor light emitting element at Block 710, at least a portion of the light emitting surface may be coated with a patternable film comprising transparent silicone and free of phosphor, for example as shown at 420 of Figure 4. Coating of Block 710 then may be performed.

Referring to Block 720 of Figure 7 and to Figure 2, if transparent photopatternable film is used, the photopatternable film comprising transparent silicone and phosphor 120 may be photopatterned to form an aperture 122 therein that exposes the light emitting surface 110a. When a printable film comprising transparent silicone and phosphor is used, the screen- or stencil-printing itself may be used to define the aperture 122, and photopatterning of Block 720 need not be performed. It will also be understood that if operations of Blocks 710 and 720 are being performed at the wafer level, these operations also may be used to define and provide dicing streets for dicing the wafer.

Referring now to Block 730 of Figure 7 and again to Figure 2, a bond pad 130 may be formed on the light emitting surface 110a in the aperture 122. Finally, at Block 740, a wire bond 140 may be bonded to the bond pad 130 opposite the light emitting surface 110a.

Referring again to Block 710 of Figure 7 and to Figures 3 and 6, coating may be performed so as to coat the patternable film comprising transparent silicone and phosphor 120 on at least a portion of the face 110a, 1110a' and on at least a portion of

the sidewall 110c, 110c'. As shown, for example, in Figure 6, these embodiments may provide a patternable film comprising transparent silicone and phosphor 120 that is thicker on at least a portion of the sidewall 110c, 110c', and, in some embodiments, at least 10% thicker, than on at least a portion of the face 110a, 110a'.

5 Figure 8 is a flowchart that illustrates operations for photopatterning according to various embodiments of the present invention, which may correspond to Block 720 of Figure 7 when a transparent photopatternable film is used. In particular, referring to Figure 8, at Block 810, the photopatternable film comprising transparent silicone and phosphor 120 is selectively exposed to define an aperture, such as the aperture
10 122 of Figure 2. Then, at Block 820, the photopatternable film comprising transparent silicone and phosphor, that has been exposed, is developed (rinsed) to form the aperture 122. Exposure and development may take place as described in the above-cited *"Information About Dow Corning® Brand Low-Stress Patternable Silicone Materials"*, or using other conventional techniques. Referring again to
15 Figure 8, at Block 830, the light emission of the light emitting device is measured and it is determined whether the light emitting device that is measured conforms to at least one predefined parameter, such as a desired emission frequency spectrum. If yes, photopatterning ends. If not, the photopatternable film comprising transparent silicone and phosphor is again developed (rinsed) at Block 820 to enlarge the
20 aperture.

Embodiments of the present invention that include Block 830 may arise from a recognition that a single development step may not fully develop (wash away) unpatterned portions of the photopatternable film comprising transparent silicone and phosphor. Accordingly, if the light emission spectrum is not satisfactory, a controlled
25 additional amount of the film, including the phosphor therein, may be removed by performing a second or subsequent development. Accordingly, individual semiconductor light emitting devices may be "trimmed" to meet a desired optical emission parameter.

Operations of Figures 7 and 8 may be performed on an individual
30 semiconductor light emitting device or on a plurality of semiconductor light emitting devices, either prior to or after dicing. For example, embodiments of Figure 5 may be fabricated according to embodiments of Block 710 of Figure 7 by coating a patternable film comprising transparent silicone and phosphor 120 on at least a portion of light emitting surfaces of a plurality of semiconductor light emitting

elements that are monolithically integrated. Thus, in some embodiments, coating and/or other operations of Figure 7 may be performed at the wafer stage prior to dicing.

Figure 9 is a flowchart of other operations that may be performed to coat,
5 which may correspond to Block 710 of Figure 7, according to other embodiments of the present invention. These embodiments also may correspond to devices of Figure 6.

In particular, referring to Figure 9, at Block 910, a plurality of semiconductor light emitting devices are mounted on a mounting tape 610 such as conventional "blue
10 tape." These devices may be singulated devices from a wafer, or a wafer may be singulated after mounting on the mounting tape 610. Optionally, as shown in Block 920, if it is desired to thickly coat the sidewalls of the devices, the mounting tape 610 may be stretched to space apart the devices. In other embodiments, the devices may be placed on the mounting tape 610 in spaced apart relation. In yet other
15 embodiments, the sidewalls may be coated without the need to space apart the devices.

Then, at Block 930, a patternable film comprising transparent silicone and phosphor 120 is formed on at least a portion of the light emitting surfaces 110a, 110a' of the plurality of semiconductor light emitting elements 110, 110' that are mounted
20 on the mounting tape 610. In some embodiments of Block 930, the patternable film comprising transparent silicone and phosphor 120 is also coated on the mounting tape 610 in the spaces 620 between adjacent semiconductor light emitting devices 110, 110', as shown in Figure 6. Moreover, in yet other embodiments at least a portion of the sidewalls 110c, 110c' are also coated with the photopatternable film comprising
25 transparent silicone and phosphor 120.

Embodiments of the present invention that were described above in connection with Figures 1-9 have described a single patternable film comprising transparent silicone and phosphor. However, any of these embodiments may also employ two or more patternable films comprising transparent silicone and phosphor. Thus, in some
30 embodiments of the present invention, a first patternable film comprising transparent silicone and a first phosphor is provided or coated on at least a portion of the light emitting surface of a semiconductor light emitting element. A second patternable film comprising transparent silicone and a second phosphor is then provided or coated on the first patternable film comprising transparent silicone and a first phosphor, opposite

the light emitting surface. Three or more layers of patternable film comprising transparent silicone and phosphor also may be provided.

The phosphors in two or more of these multiple layers may be identical or may be different. Thus, for example, a blue semiconductor light emitting device may be provided by providing a first patternable film comprising transparent silicone and green phosphor, and a second patternable film comprising transparent silicone and red phosphor on the first patternable film comprising transparent silicone and green phosphor. In other embodiments, an ultraviolet semiconductor light emitting element may be provided with separate patternable films that comprise transparent silicone and red, green and blue phosphors, respectively.

Moreover, in some embodiments, due to the competing absorption and emission processes, it may be desirable for the light emitting surface to excite the higher energy (emission) phosphors before the lower energy (emission) phosphors. Accordingly, in some embodiments of the present invention, a blue semiconductor light emitting element may be provided with a first patternable film comprising transparent silicone and green phosphor and a second patternable film comprising transparent silicone and red phosphor, so that the blue light that is emitted from the light emitting surface first interacts with the green phosphor and then interacts with the red phosphor. Separate cure and develop processes may be performed on an underlying patternable film prior to forming an overlying patternable film. Alternatively, a common cure and develop process may be performed.

Additional discussion of various embodiments of the present invention now will be provided. In particular, some embodiments of the present invention allow patternable films comprising transparent silicone to be used to add phosphor to a light emitting element. Photopatternable material can be patterned with ultraviolet light just like a photoresist material and behaves as a negative patternable material where areas that are not exposed are later washed away during development. Thus, if a phosphor such as YAG:Ce is mixed with a silicone material of this type, and the appropriate wavelength of UV light is selected, for example, to provide low absorption of the phosphor and low reflection, the formation of a vertical LED structure with a blue LED and yellow coating can provide a "white" LED. Additionally, multiple phosphors can be used for better color rendering. It will be understood that as used herein "vertical" means a general direction that is

perpendicular to the face 110a, 110a' of a semiconductor light emitting element 110, 110'.

In some embodiments of the present invention, the coating including phosphor on the semiconductor light emitting element can provide better Correlated Color
5 Temperature (CCT) control and can allow packagers to make white devices by using a white chip, as opposed to putting a glob of phosphor in the package while packaging the chip.

Moreover, as was described above in connection with Figure 8, the photopatternable film comprising transparent silicone 120 may have poor selectivity
10 when developing the pattern, in that some of the exposed region may also wash off. This can be considered an additional desirable feature in some embodiments of the invention. In particular, if too much coating is provided so that the desired optical property is not obtained, this poor selectivity may actually be used to erode away additional material to match the desired color point. This eroding away may be
15 performed at the wafer level and/or at the die level. Moreover, as was described above, depending on the wafer/chip geometries, the coating can be performed at the wafer level and/or after dicing on a blue tape.

Accordingly, some embodiments of the present invention can allow a manufacturer of a semiconductor light emitting device to open up the wire bond
20 location while coating the rest of the light emitting wafer or chip, so that a vertical geometry may be used. The patternable material also may be used as a solder mask in that it fits the temperature limits that are desired for die attach. Also, due to the poor selectivity of the developing nature (i.e., erosion of the material that should not be soluble in the developer), this feature can be used to tune in the color point.

Finally, as was described above, coating operations according to embodiments
25 of the present invention may be performed at the wafer level, at the wafer level after probing and testing and/or at the stretched tape level. At the wafer level, the wafer may be coated, initially cured, exposed and developed to open up bond pads, and, optionally, dicing streets. An optional final cure may then be performed followed by
30 wafer probing, dicing, sorting and packaging. Moreover, if a final cure has not been performed at the wafer level, the wafer may be diced, picked and tested, and material may be selectively removed to adjust the color point that was described in connection with Figure 8. A final cure then may be performed at the die level followed by sorting and packaging. At the stretched tape level, a partial stretch may be performed after

dicing, after which coating, curing, exposure and developing may be performed, followed by picking, testing and sorting as was already described.

In the drawings and specification, there have been disclosed embodiments of the invention and, although specific terms are employed, they are used in a generic and descriptive sense only and not for purposes of limitation, the scope of the
5 invention being set forth in the following claims.

What is Claimed is:

1. A semiconductor light emitting device comprising:
a semiconductor light emitting element that includes a light emitting surface;
and
a patternable film comprising transparent silicone and phosphor on at least a
5 portion of the light emitting surface.
2. A semiconductor light emitting device according to Claim 1 wherein
the patternable film comprising transparent silicone and phosphor includes an aperture
therein that exposes a portion of the light emitting surface, and wherein the
10 semiconductor light emitting device further comprises a bond pad on the exposed
portion of the light emitting surface in the aperture.
3. A semiconductor light emitting device according to Claim 2 further
comprising a wire bond on the bond pad opposite the light emitting surface.
15
4. A semiconductor light emitting device according to Claim 1 wherein
the light emitting surface includes a face and a sidewall that extends from the face,
and wherein the patternable film comprising transparent silicone and phosphor is on at
least a portion of the face and on at least a portion of the sidewall.
20
5. A semiconductor light emitting device according to Claim 4 wherein
the patternable film comprising transparent silicone and phosphor is thicker on the at
least a portion of the sidewall than on the at least a portion of the face.
- 25 6. A semiconductor light emitting device according to Claim 5 wherein
the patternable film comprising transparent silicone and phosphor is at least 10%
thicker on the at least a portion of the sidewall than on the at least a portion of the
face.
- 30 7. A semiconductor light emitting device according to Claim 1 wherein
the phosphor is configured to convert at least some light that is emitted from the light
emitting surface such that light that emerges from the semiconductor light emitting
device appears as white light.

8. A semiconductor light emitting device according to Claim 1 further comprising:

5 a patternable film comprising transparent silicone and free of phosphor, between the light emitting surface and the transparent patternable film comprising silicone and phosphor.

9. A semiconductor light emitting device according to Claim 1 wherein the semiconductor light emitting element comprises a first semiconductor light emitting element and wherein the light emitting surface comprises a first light emitting surface, the semiconductor light emitting device further comprising:

a second semiconductor light emitting element that is monolithically integrated with the first semiconductor light emitting element and that includes a second light emitting surface; and

15 wherein the patternable film comprising transparent silicone and phosphor is on at least a portion of the first and second light emitting surfaces.

10. A semiconductor light emitting device according to Claim 1 wherein the semiconductor light emitting element comprises a first semiconductor light emitting element and wherein the light emitting surface comprises a first light emitting surface, the semiconductor light emitting device further comprising:

a second semiconductor light emitting element that includes a second light emitting surface; and

a mounting tape;

25 wherein the first and second light emitting devices are on the mounting tape and spaced apart from one another; and

wherein the patternable film comprising transparent silicone and phosphor is on at least a portion of the first and second light emitting surfaces.

30 11. A semiconductor light emitting device according to Claim 10 wherein the patternable film comprising transparent silicone and phosphor extends onto the mounting tape between the spaced apart first and second light emitting devices.

12. A semiconductor light emitting device according to Claim 11 wherein the first light emitting surface includes a first sidewall facing the second semiconductor light emitting element, wherein the second light emitting surface includes a second sidewall facing the first semiconductor light emitting element and
5 wherein the patternable film comprising transparent silicone and phosphor also extends onto at least a portion of the first and second sidewalls.

13. A semiconductor light emitting device according to Claim 1 wherein the patternable film comprising transparent silicone and phosphor comprises a
10 photopatternable film transparent comprising silicone and phosphor.

14. A semiconductor light emitting device according to Claim 1 wherein the patternable film comprising transparent silicone and phosphor comprises a printable film comprising transparent silicone and phosphor.
15

15. A semiconductor light emitting device according to Claim 1 wherein the patternable film comprising transparent silicone and phosphor is a first patternable film comprising transparent silicone and a first phosphor, the device further comprising:

20 a second patternable film comprising transparent silicone and a second phosphor on the first patternable film comprising transparent silicone and a first phosphor, opposite the light emitting surface.

16. A semiconductor light emitting device according to Claim 15 wherein
25 the first phosphor comprises a green phosphor and the second phosphor comprises a red phosphor.

17. A method of fabricating a semiconductor light emitting device comprising:
30 coating a patternable film comprising transparent silicone and phosphor on at least a portion of a light emitting surface of a semiconductor light emitting element.

18. A method according to Claim 17 wherein coating comprises coating a photopatternable film comprising transparent silicone and phosphor on the at least a portion of a light emitting surface of a semiconductor light emitting element.
- 5 19. A method according to Claim 17 wherein coating comprises printing a printable film comprising transparent silicone and phosphor on the at least a portion of a light emitting surface of a semiconductor light emitting element.
- 10 20. A method according to Claim 18 further comprising:
photopatterning the photopatternable film comprising transparent silicone and phosphor to form an aperture therein that exposes a portion of the light emitting surface.
- 15 21. A method according to Claim 19 further comprising:
printing the printable film comprising transparent silicone and phosphor on the at least a portion of a light emitting surface of a semiconductor light emitting element to define an aperture therein that exposes a portion of the light emitting surface.
- 20 22. A method according to Claim 20 further comprising:
forming a bond pad on the exposed portion of the light emitting surface in the aperture.
- 25 23. A method according to Claim 21 further comprising:
forming a bond pad on the exposed portion of the light emitting surface in the aperture.
- 30 24. A method according to Claim 22 further comprising:
bonding a wire to the bond pad opposite the light emitting surface.
25. A method according to Claim 23 further comprising:
bonding a wire to the bond pad opposite the light emitting surface.
26. A method according to Claim 17 wherein the light emitting surface includes a face and a sidewall that extends from the face, and wherein coating

comprises coating the patternable film comprising transparent silicone and phosphor on at least a portion of the face and on at least a portion of the sidewall.

27. A method according to Claim 26 wherein coating comprises coating
5 the patternable film comprising transparent silicone and phosphor thicker on the at least a portion of the sidewall than on the at least a portion of the face.

28. A method according to Claim 27 wherein coating comprises coating
the patternable film comprising transparent silicone and phosphor at least 10% thicker
10 on the at least a portion of the sidewall than on the at least a portion of the face.

29. A method according to Claim 17 wherein the phosphor is configured to
convert at least some light that is emitted from the light emitting surface such that
light that emerges from the semiconductor light emitting device appears as white
15 light.

30. A method according to Claim 20 wherein photopatterning comprises:
selectively exposing the photopatternable film comprising transparent silicone
and phosphor to define the aperture; and
20 developing the photopatternable film comprising transparent silicone and
phosphor that has been exposed, to form the aperture.

31. A method according to Claim 30 further comprising:
again developing the photopatternable film comprising transparent silicone
25 and phosphor that has been developed, to enlarge the aperture.

32. A method according to Claim 31 wherein the following is performed
between developing and again developing:
measuring light emission of the light emitting device; and
30 wherein again developing is performed if the light emission of the light
emitting device that is measured does not conform to at least one predefined
parameter.

33. A method according to Claim 32 wherein the at least one predefined parameter comprises an emission frequency spectrum.

34. A method according to Claim 17 wherein coating is preceded by:
5 coating a patternable film comprising transparent silicone and free of phosphor on at least a portion of the light emitting surface.

35. A method according to Claim 17 wherein coating comprises:
coating a transparent patternable film comprising silicone and phosphor on at
10 least a portion of light emitting surfaces of a plurality of semiconductor light emitting elements that are monolithically integrated.

36. A method according to Claim 17 wherein the patternable film comprising transparent silicone and phosphor is a first patternable film comprising
15 transparent silicone and a first phosphor, the method further comprising:
coating a second patternable film comprising transparent silicone and a second phosphor on the first patternable film comprising transparent silicone and a first phosphor.

20 37. A method according to Claim 36 wherein the first phosphor comprises a green phosphor and the second phosphor comprises a red phosphor.

38. A method according to Claim 17:
wherein coating is preceded by mounting a plurality of semiconductor light
25 emitting devices including corresponding light emitting surfaces, on a mounting tape;
and

wherein coating comprises coating a patternable film comprising transparent silicone and phosphor on at least a portion of the light emitting surfaces of the plurality of semiconductor light emitting elements that are mounted on the mounting
30 tape.

39. A method according to Claim 38:
wherein the following is performed between mounting and coating:

stretching the mounting tape to define spaces between adjacent semiconductor light emitting devices; and

wherein coating comprises coating a patternable film comprising transparent silicone and phosphor on at least a portion of the light emitting surfaces of the plurality of semiconductor light emitting elements that are mounted on the mounting tape and on the spaces between adjacent semiconductor light emitting devices.

40. A method according to Claim 39 wherein the semiconductor light emitting surfaces include sidewalls and wherein coating comprises:

coating a patternable film comprising transparent silicone and phosphor on at least a portion of the light emitting surfaces of the plurality of semiconductor light emitting elements that are mounted on the mounting tape and on the spaces between adjacent semiconductor light emitting devices so as to coat at least a portion of sidewalls of the semiconductor light emitting elements with the patternable film comprising transparent silicone and phosphor.

1/2




FIG. 1




FIG. 2




FIG. 3




FIG. 4

2/2




FIG. 5





FIG. 6



INTERNATIONAL SEARCH REPORT

International application No

PCT/US2005/023874

A. CLASSIFICATION OF SUBJECT MATTER

H01L33/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 747 406 B1 (BORTSCHELLER JACOB C ET AL) 8 June 2004 (2004-06-08)	1-7,13, 17,18, 20,22, 24, 26-33, 36,37
Y	column 2, line 54 - line 61 column 8, line 5 - column 9, line 22	9,15,16, 35
X	----- EP 1 198 016 A (LUMILEDS LIGHTING U.S., LLC) 17 April 2002 (2002-04-17) paragraphs [0012] - [0016]; figures 3A-3C paragraphs [0024], [0025], [0031] paragraph [0034]; figure 6 ----- -/--	1,8,14, 17,19, 21,23, 25,34

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

2 December 2005

Date of mailing of the international search report

03 MAART 2006

Name and mailing address of the ISA/
European Patent Office, P.B. 5818 Patentlaan 2
NL-2000 LV Bilthoven

Authorized officer

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2005/023874

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 6 366 018 B1 (GARBUZOV DMITRI ZALMANOVICH ET AL) 2 April 2002 (2002-04-02) column 6, line 43 - column 7, line 21; figure 4 -----	9,35
Y	US 2002/015013 A1 (RAGLE LARRY) 7 February 2002 (2002-02-07) paragraph [0024] - paragraph [0032]; figures 4,5 -----	9,15,16, 35
A	US 6 395 564 B1 (HUANG WEN-CHIEH) 28 May 2002 (2002-05-28) figure 2 -----	1,17,19
A	US 2004/056260 A1 (SLATER DAVID B ET AL) 25 March 2004 (2004-03-25) paragraph [0029] - paragraph [0039] -----	26,27
A	US 2003/080341 A1 (SAKANO KENSHO ET AL) 1 May 2003 (2003-05-01) paragraphs [0229], [0230] paragraphs [0242], [0244]; figures 7A,7B -----	1,17,19

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2005/023874

Box II Observations where certain claims were found unsearchable (Continuation of Item 2 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box III Observations where unity of invention is lacking (Continuation of Item 3 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

see additional sheet

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1-9, 13-37

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. claims: 1-9,13-37

Semiconductor light-emitting device comprising on its light emitting surface a patternable film containing silicone and phosphor, and provided with a bond pad inside an aperture in this film

1.1. claims: 9,35

Monolithically integrated semiconductor light-emitting device comprising two light-emitting elements, their light-emitting surfaces comprising a patternable film containing silicone and phosphor

2. claims: 10-12,38-40

Semiconductor light-emitting device comprising two light-emitting elements mounted on a tape, their light-emitting surfaces comprising a patternable film containing silicone and phosphor

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2005/023874

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6747406	B1	08-06-2004	US 2004203312 A1	14-10-2004
EP 1198016	A	17-04-2002	JP 2002185048 A	28-06-2002
			US 6650044 B1	18-11-2003
			US 2004097006 A1	20-05-2004
US 6366018	B1	02-04-2002	AU 1451000 A	08-05-2000
			CA 2347627 A1	27-04-2000
			CN 1324494 A	28-11-2001
			EP 1141990 A1	10-10-2001
			JP 2002528890 T	03-09-2002
			WO 0024024 A1	27-04-2000
US 2002015013	A1	07-02-2002	US 2004222735 A1	11-11-2004
US 6395564	B1	28-05-2002	DE 10135306 A1	22-08-2002
			GB 2372149 A	14-08-2002
			JP 2002246654 A	30-08-2002
			TW 490863 B	11-06-2002
US 2004056260	A1	25-03-2004	NONE	
US 2003080341	A1	01-05-2003	CN 1455960 A	12-11-2003
			CN 1665041 A	07-09-2005
			CN 1670076 A	21-09-2005
			EP 1357610 A1	29-10-2003
			WO 02059982 A1	01-08-2002
			JP 3428597 B2	22-07-2003
			SG 112904 A1	28-07-2005
			US 2005224821 A1	13-10-2005